

## Defoamer

Chemical comp. : Preparation of silicone oil and emulsifiers  
Ionic character : Nonionic  
Appearance : White liquid  
pH range : 8,0- 9,0

## Properties

- Defoamer for dyeing, finishing or sizing liquors
- High stability of emulsion in application bathes
- Suited for jet equipment (particularly if there occurs strong circulation of liquor)
- May be applied in combination with anionic and cationic dyes and products
- Does not affect wetting, washing or bleaching agents

## Application

DUPOL SB might be diluted with cold water prior to addition  
Stock solution of ratios 1:3 – 1:10 may be produced

We recommend to add to the liquors:

DUPOL SB : 0,1 – 0,4 g/l  
Printing paste : 1 – 4 g/kg

Exhaust process: 0.2 –0.5 g/L

Storage: Storage life is one year in original packing and at room temperature.

Storage and transport not below +3 °C and not over +30 °C-

Otherwise product shouldn't be used anymore

Packing: 120 kg plastic drum

## Köpük Kesici

Kimyasal yapısı : Silikon yağı ve emülsiyeciler  
İyonik yapısı : Noniyonik  
Görünüm : Beyaz sıvı  
pH aralığı : 8,0-9,0

## Özellikler

- Boya, finish ve haşıl banyoları için köpük kesicidir.
- Uygulama banyolarında yüksek emülsiyon stabilitesi
- Jet uygulamasına ve yüksek devirli banyolara uygundur.
- Anyonik ve katyonik boya ve diğer yardımcı kimyasalların kombinasyonlarında uygulanabilir.
- Islatıcı, yıkayıcı ve beyazlatıcı kimyasallara herhangi bir yan etkisi yoktur.

## Uygulama

DUPOL SB, soğuk su ile seyreltilerek kullanılabilir.  
Ürün, 1:3-1:10 aralığında seyreltilerek stok solüsyon hazırlanabilir.

Reçete önerileri:

DUPOL SB : 0,1 – 0,4 g/l  
Baskı patı : 1 – 4 g/kg

Çektirme prosesi: 0,2-0,5 g/L

Depolama: Orijinal ambalajlarında ve uygun depolama şartlarında depolama ömrü 1 yıldır.

Kapalı ambar tavsiye edilir. +3 °C ve +30 °C arasında saklanmalı ve depolanmalıdır.

Ambalaj: 120 kg plastik bidon,IBC

These information, suggestion and examples are based on our current laboratory and practical experience and composed for purpose of leading users about our products and not considered legally binding.

Bu prospektüste sunulan bilgi, örnek ve öneriler; uygulayıcılara ürünlerimiz hakkında yol göstermek amacıyla güncel laboratuvar ve işletme deneyimlerimize dayanarak oluşturulmuş olup hukuki bağlayıcı bir garanti ifade etmez.