

Wetting agent

Chemical comp. : Mixture of surfactants
Ionic character : Nonionic
Appearance : Clear liquid
pH range : 6,0-7,0 ?

Properties

- Low-foaming, alkali-resistant washing and wetting agent with excellent dispersing power for pre-treatment and dyeing of all fibre types
- It is used in cellulosic, synthetic fiber and all kinds of blends.
- It provides hydrophilicity to the fabric by removing oil, wax and pectins from the fabric.
- It is suitable for use in continuous and exhaust systems.
- It is suitable for use with anionic, nonionic materials.
- It can be used for pre-wetting or for improving penetration and wetting in all pre-treatment processes.
- It has high emulsifying and dispersing properties.

Application

Easily soluble with water.

Exhaust process : 0.2 -1.0 g/l
Continuous process : 0.4 -3.0 g/l

Storage: Storage life is one year in original packing and at room temperature.

Storage and transport not below +3 °C and not over +30 °C-

Otherwise product shouldn't be used anymore

Packing: 120 kg plastic drum, IBC

Islatıcı

Kimyasal yapısı : Yüzey aktif maddelerin karışımı
İyonik yapısı : Nonyonik
Görünüm : Berrak sıvı
pH aralığı : 6,0-7,0 ?

Özellikler

- Her türlü elyafın ön işleme ve boyanması için mükemmel dispersiyon gücüne sahip, düşük köpüren, alkaliye dayanıklı yıkama ve ıslatma maddesidir.
- Selülozik, sentetik elyaf ve her türlü karışımda kullanılır.
- Kumaştan yağ, vaks ve pektinleri uzaklaştırarak kumaşa hidrofiliklik sağlar.
- Kontinü ve çektirme sistemlerinde kullanıma uygundur.
- Anyonik, nonyonik ürünlerle kullanıma uygundur.
- tüm ön işlem süreçlerinde penetrasyon ve ıslatma.
- Yüksek emülsifiye edici ve dispersiyon özelliklerine sahiptir.

Uygulama

Su ile kolayca seyreltilebilir.

Çektirme Proseslerinde : 0.2 -1.0 g/l
Kontinü Proseslerinde : 0.4 -3.0 g/l

Depolama: Orijinal ambalajlarında ve uygun depolama şartlarında depolama ömrü 1 yıldır.

Kapalı ambar tavsiye edilir. +3 °C ve +30 °C arasında saklanmalı ve depolanmalıdır.

Ambalaj: 120 kg plastik bidon,IBC

These information, suggestion and examples are based on our current laboratory and practical experience and composed for purpose of leading users about our products and not considered legally binding.

Bu prospektüste sunulan bilgi, örnek ve öneriler; uygulayıcılara ürünlerimiz hakkında yol göstermek amacıyla güncel laboratuvar ve işletme deneyimlerimize dayanarak oluşturulmuş olup hukuki bağlayıcı bir garanti ifade etmez.